

THE INFLUENCE OF THE QUALITY OF WATER ON THE MECHANICAL PROPERTIES BRICKS OF EARTH. (THE CASE OF SEBKHA OF AIN EL BAIDA)

Hachem CHAIB^{a,*}, Abdelouahed KRIKER^a, Saci, DAHMANI^a

^a Laboratory of exploitation and valorization of natural resources in arid zones, Ouargla 30000, Algeria

chaib.hachem.dz@gmail.com

Abstract

The present work, aims to study the influence of the quality of the mixing water of a few drilling in the south-eastern region of Algeria on the mechanical properties of the bricks of land. These bricks are made on the basis of materials of construction of this local region (clay, sand dunes).

In this study, we proposed the water of sebkha of Ain el Baiba

Key words: water, sebkha, mechanical properties, brick.

1. INTRODUCTION

The Laboratory of exploitation and exploitation of natural resources in arid zone (E.V.R.N.Z.A) of the University of Ouargla (Algeria) follows a program of research and study of thermal insulation of few construction materials usually used in the Saharan regions as "The Red Brick", in view of a contribution to the improvement of the Properties thermo-mechanical systems of construction materials in the Saharan areas.

We have proposed a comparative study of a few drilling in our region on the properties thermo-mechanical.

2. Materials and Methods

2.1. The SAND DUNES

For our study we used the sand dunes of Sidi-Khouiled (Ouargla). We have carried out the following tests:

- The mass density absolute
- The apparent volumic mass
- Equivalent of sand
- Chemical analysis

These analyzes are conducted at the Laboratory of Civil Engineering from the University of Kasdi Merbah Ouargla, for all the tests we have used three samples in each characteristic. The results obtained are the following:

Table 1. Physical characteristics of sand dunes

Tests	Result
The mass density absolute	$\rho_s = 2560 \text{ kg/m}^3$
The apparent volumic mass	$\rho_a = 1512.5 \text{ kg/m}^3$
Equivalent of sand	ESp=99,+23%

Chemical analysis

The following table shows the percentages of chemical components of sand dunes. This analysis is conducted in the Laboratory of Public Works of the South (L.T.P.S) unit of Ouargla.

Table 2. Chemical compositions of sand

The components	Percentages (%)
Fe 2O3 - Al2 O3	0.25
Ca SO4, 2H2O	2.78
SO4	0.51
Ca CO3	1.30
Insoluble	93.23
Na Cl	Trace
Loss at the fire	1.16

We note that the percentage of (Ca SO4), (SO4) is less than the limit recommended. Of this fact the sand used is non-aggressive.

2.2. The clay

For this research we have used the clay to Touggourt at Ouargla. We have carried out the following tests on the clay:

- Dry density
- Blue of methylene
- Limit of Atterberg
- Chemical analysis

These tests are carried out at the Laboratory of Public Works of the South (L.T.P.S) unit of Ouargla. The results are in Table 3.

Table 3. Physical characteristics of sand dunes

Characteristics	Result
The dry density (NF P 94/064)	$P = 2.03 \text{ g/cm}^3$
Methylene blue (NF EN 933-9)	VBS = 8
Limit of Atterberg (NF P 94-051)	$W_L = 69.58\%$
	$W_P = 24.71\%$
	$I_P = 44.87\%$

Chemical analysis

The main results of the chemical analysis carried out are grouped in the following table:

Table 4. Chemical compositions of the clay

Chemical Characteristics	The components	Percentages (%)
Insoluble (NF P 15 - 461)	Insoluble	63.18
Sulphate (BS 1377)	SO_3	0.45
	$\text{Ca SO}_4 / 2\text{H}_2\text{O}$	2.46
The carbonates (NF P 15 - 461)	CaCO_3	18.0
Chlorides (method of MOHR)	Cl^-	0.42
	NaCl	0.68

The table shows that the elements of this clay are insoluble in percentage of approximately 64%, the levels of sulphates and chlorides are very low.

2.3. The water of GACHAGE

The mixing water serves on the one hand to the hydrations of cement and on the other hand allows the fluidization of the dough, that the water Between in contact with the clay anhydrous, it reacts to form hydrates of clay.

2.3.1. TYPE OF waters used

a. Distilled water

Distilled water is water that has undergone a distillation, therefore is theoretically free of some minerals and agencies that could be found in the water "natural." Possibility to filter the water in distilled using several methods, such as reverse osmosis, carbon filter, and UV oxidation or electrodialysis, distilled water is used in several fields of science, engineering laboratory and industrial, because it does not contain impurities and salts, which cause deposits in the tools and equipment, leading to damage, and is used in more in the pipelines.

b. Tap water

The tap water used is the water of the laboratory of civil engineering of the University of Kassedji Merbah, Ouargla. This water is extracted from a groundwater Mio-Pliocene called.

Table 6. Chemical composition of the tap water

Ca ⁺²	Mg ⁺²	K ⁺	Na ⁺	Cl ⁻	No. ³⁻	SO ₄ ⁻²	HCO ³⁻	PH
264.53	106.92	25	515.2	795.2	13.5	818.57	97	7.77

The concentrations are data in mg/l.

The conductivity 4.560 ms/cm

The résidée sec to 105 0C 2844 mg/l

$$TH = ([Ca^{+2}] \text{ meq/L} + [Mg^{+2}] \text{ meq/l}) \cdot 50 = 1106,5 \text{ mg/lCaCo}_3$$

This water is very hard and may salt has a pH acceptable.

c. Water of sebkha

This sample is extracted from a drain dug in the Sebkha of Ain el Baida, on the road of the heavy weight. The water of this groundwater is less than 30cm of the surface. It is a water without smell, neither color, salty not reserved for human consumption.

In the southern regions the groundwater is at a depth of 0.8 to 1 m according to the areas and seasons.

Table 7. Chemical composition of the water of sebkha

Ca ⁺²	Mg ⁺²	K ⁺	Na ⁺	Cl ⁻	No. ³⁻	SO ₄ ⁻²	HCO ³⁻	PH
801.6	1117.8	150	5623.5	8679.75	0.876	5631.24	160	8.35

The concentrations are data in mg/l.

The conductivity 100.000 ms/cm

The résidée sec to 105 0c 23796 mg/l

$$TH = ([Ca^{+2}] \text{ meq/L} + [Mg^{+2}] \text{ meq/l}) \cdot 50 = 6661,5 \text{ mg/lCaCo}_3$$

This water is very bad to the consumption for its hardness and its salinity Very High

3. Results and Discussion

We have proposed for our work the three compositions (Clay+sand):

- Composition C1 :70% clay +30%sand (distilled water)
- Composition C2: 70% clay +30%sand (tap water)
- Composition C3 70% clay +30%sand (the water of sebkha)

The tests were performed on bricks of dimensions (200×100×50 mm), the results are grouped in the Table 8.

Table 8. The results of the compositions

Measuring cylinder (brick)	C1	C2	C3
The mass M (kg)	1.45	1.43	1.38
Thermal conductivity λ (W/m°C)	0.64	0.63	0.57
Thermal Resistance R _{th} (M°C/W)	0.070	0.071	0.075
Resistance to traction	1.34	1.19	0.98
Resistance to compression	4.81	3.2	2.18

After the results obtained we note that:

- A remarkable reduction of the thermal conductivity in the bricks C3 and it is due to the high salinity of the mixing water in the mixture.
- The thermal resistance will automatically increase in the bricks C3, this is logical in view of the fact that theoretically r_{th} varies in the opposite direction that λ .
- The resistance to bending the highest is that of the composition (C1) is it is due to the use of the distilled water that gives a good cohesion of the matrix of the mixture.

4. CONCLUSION

According to this experimental study, we can draw the following conclusions:

- A remarkable reduction of the thermal conductivity in the bricks C3 and it is due to the high salinity of the mixing water in the mixture.
- The thermal resistance will automatically increase in the bricks C3, this is logical in view of the fact that theoretically r_{th} varies in the opposite direction that λ .
- The resistance to bending the highest is that of the composition (C1) is it is due to the use of the distilled water that gives a good cohesion of the matrix of the mixture.

Reference

- [1] Document, 'Data Sonelgaz'.
- [2] MEKHERMECHE has "Contribution to the study of the mechanical and thermal properties of the bricks in the land with a view to their use in the restoration of the Saharan Ksour." thesis of Magister University of Ouargla 2012.
- [3] ENAG "Recommendation architectural" edition book Algiers 1993.
- [4] KRIKER has "Characterization of the fibers of date palm and properties of concretes and mortars strengthened by these fibers in hot and dry climate "Doctoral thesis of State OE 2005.
- [5] Bedzki, AK, Gassan J. composites reinforced with cellulose based fibers. Prog Polym Sci 1999; 24:221-274.
- [6] LEMOUGNA NINL P. "contribution to the decrease of broken in the production of bricks of the terracotta to the PROMOBAT "
- [7] Swamy RN. Vegetable fiber reinforced cement composite a false dream or a potential reality. In: Sobral H.S, editor. Proceedings of the Second International RILEM Symposium, vegetable plants and their fibers as building materials, Salvaor, Bahia (Brazil), Chapman and Hall; 1990: p. 139-49.
- [8] Hanifi B, Orhan has, Mehmet N, Erhan has, Selim K. Insulation thermal and mechanical properties of fiber reinforced mud bricks as wall materials. Construction and Building Materials; 2007: 21: 901-906.
- [9] Abani S. Characterization of concretes reinforced by vegetable fibers of date palm. Memory of magister; University of Ouargla 2003.
- [10] Ghavami K, Filho RTD, Barbosa NP. Behavior of composite soil reinforced with natural fibers. Concrete EMC dial 1999; 21(1):39-48.
- [11] Coutts RSP, nor Y. Autoclaved bamboo pulp fiber reinforced cement. Concrete EMC dial 1995; 17(2):99-106.
- [12] Taallah B., Guettala A., Guettala S, Kriker A. mechanical properties and hygroscopicity behavior of compressed earth block filled by date palm fibers. Construction and Building Materials 59 (2014) 161-168
- [13] Al-Harthy AS, Abdel Halim M, Taha R, Al-Jabri KS. The properties of concrete made with fine sand dune. Constr Build Mater 2007; 21:1803-8.
- [14] Djoudi A. Structural characterization rheological and of concrete plaster and their strengthening by the vegetable fibers of the date palm. Thesis magister; University El Laghouat; 2001.
- [15] Arnaud R. The measurement of thermal conductivity. Ecole des Mines de Paris: Center for Energy and Processes.